

Pad printing ink for ABS, rigid PVC, pre-treated polyethylene/polypropylene, varnished surfaces, thermosetting plastics, metal

Glossy, good opacity, fast drying 1 or 2 component system, resistant to chemicals

Vers. 10
2015
24. Apr

Field of Application

Substrates

Tampa® Pol TPY is particularly suited to print onto

- ABS
- rigid PVC
- Wood, Paper, and cardboard

By adding hardener, Tampa® Pol TPY adheres excellently to many other substrates such as

- pre-treated polyethylene (PE)
- pre-treated polypropylene (PP)
- Thermosetting plastics
- Metal
- varnished surfaces
- Polyamide (PA)

Since all the print substrates mentioned may be different in printability even within an individual type, preliminary trials are essential to determine the suitability for the intended use.

Field of use

Tampa® Pol TPY is mainly used to print onto packaging made of polyethylene, polypropylene or rigid PVC.

When printing onto polyethylene or polypropylene, please make sure to pre-treat the surface of your substrate by flaming or Corona discharge as usual.

As per our experience, you can achieve a very good adhesion with the Tampa® Pol TPY with a surface tension of at least 42-48 mN/m. On polypropylene, you can also apply a thin film of our colourless Primer P 2 for surface pre-treatment.

For multiple colour printing, please consider that you should not flame the substrate between print sequences, as this may reduce intercoat adhesion.

Characteristics

Ink Adjustment

The ink should be stirred homogeneously before printing and if necessary during production.

Use as 2-component ink

Depending upon the substrate and the requirements, hardener can be added to the ink before printing.

Pre-reaction time

It is recommended to allow the ink/hardener mixture to pre-react for 15 minutes.

Pot life

The ink/hardener mixture is chemically reactive and must be processed within 12-14 h (H 1) bzw. 8-10 h (H 2) (referred to 20° C and 50% RH). Higher temperatures reduce the pot life. If the mentioned times are exceeded, the ink's adhesion and resistance may be reduced even if the ink still seems processable.

With the use of HT 1, there is no pot life to consider since this hardener is only activated by a baking process (30 min/150° C).

Parallel to physical drying (i. e. to the evaporation of the solvents used), the actual hardening of the ink film is caused by the chemical cross-linking reaction between ink and hardener.

For Hardeners H 1 and H 2, this reaction can be accelerated by higher temperatures, in the case of HT 1 it is a must. When using hardener, the processing and curing temperature must not be lower than 15°C as irreversible damage can occur. Please also avoid high humidity for several hours after printing as the hardener is sensitive to humidity.



Drying

Physically fast drying. Touch-dry at 20° C after approx. 2 min, at 30°C after approx. 30-40 sec. The addition of Hardener H 1 or H 2 will extend the drying time. The times mentioned above vary according to substrate, depth of cliché, drying conditions, and the auxiliaries used.

Fade resistance

Only pigments of high fade resistance are used in the Tampa® Pol TPY range. Shades mixed by adding overprint varnish or other colour shades, and especially white, have a reduced fade and weather resistance depending on their mixing ratio. The fade resistance also decreases if the printed ink film thickness is reduced. The pigments used are resistant to solvents and plasticizers.

Stress resistance

After proper and thorough drying, the ink film exhibits outstanding adhesion as well as rub, scratch, and block resistance and is resistant to oils, greases, aqueous acids, alkalines, and alcohol.

Range

Basic Shades

920	Lemon
922	Light Yellow
924	Medium Yellow
926	Orange
930	Vermilion
932	Scarlet Red
934	Carmine Red
936	Magenta
940	Brown
950	Violet
952	Ultramarine Blue
954	Medium Blue
956	Brilliant Blue
960	Blue Green
962	Grass Green
970	White
980	Black

4-Colour Process Shades Standard

429	Process Yellow
439	Process Magenta
459	Process Cyan
489	Process Black

High Opaque Shades

122	High Opaque Light Yellow
130	High Opaque Vermilion
152	High Opaque Ultramarine Blue
162	High Opaque Grass Green

Press-Ready Metallics

191	Silver
192	Rich Pale Gold
193	Rich Gold

Further Products

910	Overprint Varnish
-----	-------------------

Mixtures of TPY 191-193 with TPY 950 or TPY 952 have a limited shelf life. Due to this, please prepare only such quantities which will be processed in the course of 4-5 days (20°C).

All shades are intermixable. Mixing with other ink types or auxiliaries must be avoided in order to maintain the special characteristics of this ink.

All basic shades are included in our Marabu-ColorFormulator (MCF). They build the basis for the calculation of individual colour matching formulas, as well as for shades of the common colour reference systems HKS®, PANTONE®, and RAL®. All formulas are stored in the Marabu-ColorManager software.

Additionally there are high-opaque formulas available marked with + + behind the reference name. These formulas have been developed by using the System Tampacolor formulas for basic and high-opaque shades excluding the semi-transparent, resp. transparent shades.

Metallics

Metallics which are suited for 1 k applications:

Metallic Powders

S 181	Aluminium	17%
S 182	Rich Pale Gold	25%
S 183	Rich Gold	25%
S 184	Pale Gold	25%
S 186	Copper	33%
S 190	Aluminium, rub-resistant	12.5%



For 2 k applications, only S 181 Aluminium and S 190 Aluminium (wipe resistant) can be used. The gold shades are not processable with hardener (max. pot life approx. 30 minutes).

These metallics are added to TPY 910 in the recommended amount, whereas the addition may be individually adjusted to the respective application. We recommend preparing a mixture which can be processed within a maximum of 8 h since metallic mixtures usually cannot be stored. Due to their chemical structure, the processing time of mixtures with Pale Gold S 184 and Copper S 186 is even reduced to 4 h.

Owing to the bigger pigment size of Metallic Powders we recommend the use of a halftone cliché with a minimum depth of 25-30 µm. Shades made of Metallic Powders are always subject to an increased dry abrasion which can only be reduced by overvarnishing. All metallic shades are displayed in the Marabu "Screen Printing Metallics" colour chart.

Auxiliaries

TPV	Thinner	15-25%
TPV 2	Thinner, fast	15-25%
TPV 7	Thinner	15-25%
TPV 3	Thinner, slow	15-20%
H 1	Hardener	10%
H 2	Hardener, fast	10%
HT 1	Hardener, heat-reactive	10%
MP	Matting Powder	2-4%
ES	Printing Modifier	0.5-1%
OP 170	Opaquing Paste	0-15%
AP	Antistatic Paste	0-10%
VP	Retarder Paste	0-10%
UR 3	Cleaner (flp. 42°C)	
UR 4	Cleaner (flp. 52°C)	
UR 5	Cleaner (flp. 72°C)	
SV 1	Retarder	
P 2	Primer	

Thinner is added to the ink to adjust the printing viscosity.

TPV 7 is an all-purpose thinner for improved ink transfer for fast printing. It features good mixing and solving properties, combined with a long processing period.

For slow printing sequences and fine motifs, it

may be necessary to add retarder to the thinner. For an additional thinning of the ink containing retarder, only pure thinner should be used. An excessive addition may result in ink transfer problems.

Hardener H 1 and H 2 are sensitive to humidity and always to be stored in a sealed container. H 1 or H 2 can be added for increased resistance and adhesion. Shortly before use, the hardener is added to the ink and stirred homogeneously. The mixture ink/hardener is not storable and must be processed within pot life.

Hardener HT 1 is also sensitive to humidity and is always to be stored in a sealed container. If using HT 1, there is no pot life to consider since this hardener is only activated by a baking process (30 min/150°C).

By adding Matting Powder MP the ink film can be matted individually (preliminary trials in terms of adhesion and resistance are essential, white shades addition max. 2%).

Printing Modifier ES contains silicone and can be used to rectify flow problems on critical substrates. If an excessive amount is added, flow problems are increased and adhesion may be reduced, especially when overprinting. The use of ES may reduce the degree of gloss.

By adding Opaquing Paste 170, the opacity of colour shades can significantly be increased without considerably influencing the chemical and dry abrasion resistance. OP 170 is not suitable for white shades, and should not be used for prints that will be exposed to more than 2 years outdoor application.

The addition of Antistatic Paste AP reduces the impact of static charge on the ink. It lowers the viscosity of the ink and non-polar components help to avoid "stringy" behaviour when printing onto non-polar substrates.

The cleaners UR 3 and UR 4 are recommended for manual cleaning of the working equipment. Cleaner UR 5 is recommended for manual or automatic cleaning of the working equipment. Special Primer P 2 is used for manual pre-cleaning and pre-treatment of PP substrates.



Printing Parameters

Clichés

All commercially available clichés made of ceramic, photopolymer, thin steel, and chemically hardened steel (10 mm) can be used. The recommended cliché depth is 20-28 µm.

Printing pads

As per our experience, all common printing pads consisting of materials cross-linked by condensation or addition can be used.

Printing machines

Tampa® Pol TPY is suitable for closed ink cup systems, as well as for open ink wells. Depending on type and usage of the machine, it is to accordingly adjust type and amount of the thinner used.

Note

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor their suitability for each application.

You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us and utilised by you with respect to any and all damages not caused intentionally or by gross negligence.

Labelling

For Tampa® Pol TPY and its auxiliaries, there are current Material Safety Data Sheets available according to EC regulation 1907/2006, informing in detail about all relevant safety data including labelling according to the present EEC regulations as to health and safety labelling requirements. Such health and safety data may also be derived from the respective label.